

System Test no. 1.25_YSR_DRY				Results								
Turf pile height	Turf Description	Brock Product	TEST	ASTM F355-A Gmax	Deltec Vertical Def.	EN14808 Force Reduction	Deltec Field Tester - Energy Restitution	TEST	ASTM F355-E HIC	ASTM F355-E Gmax		
1.5"	74 oz slit film with nylon hatch	PowerBase YSR	1.5 lbs / sq. ft. Zeofill - DRY									
			POSITION 1: CENTER OF SAMPLE							Drop 1	726	0
			Drop 1	82.0	8.50	70%	27%	Drop 2	748	0		
			Drop 2	92.0	8.10	67%	29%	Drop 3	700	0		
			Drop 3	92.0	8.30	67%	31%					
			<b>AV. POS 1</b>	<b>92.0</b>	<b>8.20</b>	<b>67%</b>	<b>30%</b>	<b>Average</b>	<b>724</b>	<b>0</b>		
			POSITION 2: RIGHT CENTER OF SAMPLE									
			Drop 1	77.0	8.90	69%	25%					
			Drop 2	88.0	8.50	65%	30%					
			Drop 3	90.0	8.50	65%	31%					
			<b>AV. POS 2</b>	<b>89.0</b>	<b>8.50</b>	<b>65%</b>	<b>31%</b>					
			POSITION 3: LEFT CENTER OF SAMPLE									
			<b>OVERALL AVERAGE</b>	<b>90.5</b>	<b>8.4</b>	<b>66%</b>	<b>30%</b>					

System Test no. 1.25_YSR_WET				Results								
Turf pile height	Turf Description	Brock Product	TEST	ASTM F355-A Gmax	Deltec Vertical Def.	EN14808 Force Reduction	Deltec Field Tester - Energy Restitution	TEST	ASTM F355-E HIC	ASTM F355-E Gmax		
1.5"	74 oz slit film with nylon hatch	PowerBase YSR	1.5 lbs / sq. ft. Zeofill - WET									
			POSITION 1: CENTER OF SAMPLE							Drop 1	619	0
			Drop 1	81.0	9.20	72%	27%	Drop 2	650	0		
			Drop 2	86.0	9.00	71%	28%	Drop 3	682	0		
			Drop 3	84.0	9.20	70%	30%					
			<b>AV. POS 1</b>	<b>85.0</b>	<b>9.10</b>	<b>71%</b>	<b>29%</b>	<b>Average</b>	<b>666</b>	<b>0</b>		
			POSITION 2: RIGHT CENTER OF SAMPLE									
			Drop 1	83.0	9.40	68%	26%					
			Drop 2	89.0	8.90	66%	30%					
			Drop 3	93.0	8.70	65%	30%					
			<b>AV. POS 2</b>	<b>91.0</b>	<b>8.80</b>	<b>66%</b>	<b>30%</b>					
			POSITION 3: LEFT CENTER OF SAMPLE									
			<b>OVERALL AVERAGE</b>	<b>88.0</b>	<b>9.0</b>	<b>68%</b>	<b>30%</b>					